Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

 (Currently Amended) A heat resistant magnesium die casting alloy eemprising consisting essentially of, by wt%, the following composition:

Al: over 6% to not more than 10%,

Ca: 1.8 over 2% to 5%,

Sr: 0.05-0.05% to 1.0%,

Mn: 0.1-0.1% to 0.6%, and

Bal: Mg and unavoidable impurities,

the Ca/Al ratio of the Ca content to the Al content being 0.3 to 0.5.

- (Canceled)
- (Original) A heat resistant magnesium die casting alloy as set forth in claim 1, wherein Ca: 2.5 to 3.5%.
- (Previously Presented) A heat resistant magnesium die casting alloy as set forth in claim 1, further comprising a rare earth metal in an amount of 0.1 to 3 wt%.
- (Previously Presented) A die cast product comprised of a magnesium alloy as set forth in claim 1.
 - 6. (Canceled)
- (Previously Presented) A heat resistant magnesium die casting alloy as set forth in claim 3, further comprising a rare earth metal in an amount of 0.1 to 3 wt%.
 - 8. (Canceled)
- (Previously Presented) A die cast product comprised of a magnesium alloy as set forth in claim 3.

 (Previously Presented) A die cast product comprised of a magnesium alloy as set forth in claim 4.